

APPLICATION FOR A UNITED STATES PATENT

UNITED STATES PATENT AND TRADEMARK OFFICE

(B&D Docket No. 301500.1004-123)

Date: August 25, 2003 Express Mail Label No. ER 094113794 US

Title: FILTERS EMPLOYING POROUS STRONGLY ACIDIC POLYMERS

Inventors: Oleg Kishkovich, a citizen of United States of America and a resident of Greenville, Rhode Island 02828;
Robert W. Rezukey, a citizen of United States of America and a resident of North Grafton, Massachusetts 01536; and
Devon Kinkead, a citizen of United States of America and a resident of Holliston, Massachusetts 01746;

Assignee: Extraction Systems, Inc.
Franklin, Massachusetts

CROSS REFERENCES TO RELATED APPLICATIONS

The present application is a divisional of U.S. Patent Application No. 10/178,424, filed on June 24, 2002 which will issue on August 26, 2003 as U.S. Patent No. 6,610,128, which is a divisional of U.S. Patent 6,447,584, issued on September 10, 2002, which
5 claims the benefit of U.S. Provisional Application No. 60/097,215, filed on August 20, 1998, the entire teachings of which are incorporated herein by reference.

BACKGROUND OF THE INVENTION

In this age of increased air pollution, the removal of chemicals from the air we breathe is a concern of everyone. In addition, in the fabrication electronic materials and
10 of devices such as semiconductors, there is a requirement for uncontaminated air of high quality.

Gas phase filtration is commonly accomplished using activated carbon manufactured in various ways. One approach uses a carbon/adhesive slurry to glue the carbon to the substrate. The adhesive decreases carbon performance by forming a film on
15 its surface.

A second approach involves carbonizing an organic based web by heating, followed by carbon activation. This material is expensive and has relatively low adsorption capacity.

A third approach involves forming a slurry of carbon powders and fibers into
20 sheets by a process analogous to a wet papermaking process. This material has a medium-to-high cost, and has an undesirable high pressure drop. Moreover, chemically impregnated carbon particles cannot be efficiently used in conjunction with an aqueous process, as the aqueous nature of the process either washes away the chemical used to impregnate the carbon, or reacts undesirably with the impregnating or active chemical
25 groups thereby rendering it inoperative. In general, however, filter materials which do not incorporate chemically active groups perform far less effectively than those which do include chemically active groups.

None of these approaches fully achieve the desired properties which provide a clean, cost effective, high efficiency, low pressure drop, adsorptive composite.

SUMMARY OF THE INVENTION

The present invention comprises a clean, cost effective, high efficiency, low pressure drop, adsorptive, filter comprising a high surface area, highly acidic chemically impregnated adsorbent. A preferred embodiment of the invention can employ a non-woven composite material having acidic functional groups that bind to airborne bases. The invention can be used in lithography systems which employ materials that are sensitive to impurities, such as molecular bases present in the air circulating through semiconductor wafer processing equipment. A large number of bases including ammonia, NMP, triethylamine pyridine, and others, can be maintained at concentrations below 2 ppb in a tool cluster filtered with the present invention. The invention also includes methods for forming the filter comprising, for example, the dry application of an active adsorbent to a non-woven carrier material, which is then heated and calendered with cover sheets.

In a preferred embodiment of this invention the non-woven carrier materials can be polyester non-wovens, and the adsorbent can include sulfonated divinyl benzene styrene copolymer. Another preferred embodiment employs carboxylic functional groups. The acidic groups have a least 1 milliequivalent/gram acidity level or higher and preferably at least 4.0 milliequivalents/gram or higher. The polymers used are porous, preferably having a pore size in the range of 50-400 angstroms and a surface area of 20m²/g or higher.

The dry processing of a non-woven polyester batting allows for even distribution of adsorbent particles throughout the depth of the polyester batting. This provides an increased bed depth at a very low pressure drop, which is highly desirable since a twofold increase in depth can increase the filter's breakthrough time (time to failure) fourfold when using these thin fabric based sulfonic beds.

Thus, the invention provides a clean, cost effective, high efficiency, low pressure drop, adsorptive non-woven filter composite, and a method for forming said composite. The novel filter composite is particularly useful for the removal of base contaminants in an air stream, which contaminants can be gaseous or vaporous. Particulates will also be

removed if greater than the pore size of the filter. The filter has a service life of at least 12 months with a pressure drop to reduce power consumption and minimize impact on the systems operation. For example, a high pressure drop filter can require a longer time for a lithography system to equilibrate the temperature and humidity after filter
5 replacement.

In an alternative embodiment, the filter uses both sulfonated divinyl benzene styrene copolymer and an activated carbon as the adsorbent. Activated carbon is discussed in greater detail in U.S. Patent No. 5,582,865 title "Non-Woven Filter Composite", issued December 10, 1996 with Rezuze, et al., as inventors. The entire
10 contents of this patent is incorporated herein by reference. The filter in this preferred embodiment has two (or more) layers, one of activated carbon and one of sulfonated divinyl benzene styrene copolymer beads. Additionally, two or more materials can be mixed to provide the filter system of the present invention.

In another preferred embodiment a synthetic carbon material, such as that
15 described in U.S. Patent No. 5,834,114, entitled "Coated absorbent fibers", issued November 10, 1998 with Economy, et al., as inventors, the contents of which are incorporated herein by reference, can be coated with the materials of the present invention to provide a porous acidic filter in accordance with the invention.

A detection system and method of use for determining when the filter needs to be
20 replaced by detecting base contaminants in air is described in U.S. Patent 6,207,460 entitled "Detection of Base Contaminants in Gas Samples", issued March 27, 2001 with Oleg Kishkovich, et al as inventors. Also U.S. Patent 6,096,267 entitled "Detecting of Base Contaminants", filed issued August 1, 2000 with Oleg Kishkovich, et al as inventors and U.S. Patent 6,296,806 entitled "Protection of Semiconductor Fabrication
25 and Similar Sensitive Processes", issued October 2, 2001 with Oleg Kishkovich, et al as inventors can also be used with the present invention. These patents disclose the protection of a DUV lithography processes using chemically amplified photoresists which are sensitive to amines in the air. These patents are incorporated in the present application in their entirety by reference.

A preferred embodiment of a method of fabricating a filter element having large surface area and the desired flow characteristics involves the use of a powdered material that is deposited in sequential layers one on top of the other. Following the deposit of each layer of powdered material, a binder material is delivered onto each layer of

5 powdered material using a printing technique in accordance with a computer model of the three dimensional filter element being formed. Following the sequential application of all of the required powder layers and binder material to form the part in question, the unbound powder is appropriately removed, resulting in the formation of the desired three dimensional filter element. This technique provides for the fabrication of complex

10 unitary or composite filter elements having high surface area that are formed with a very high degree of resolution.

BRIEF DESCRIPTION OF THE DRAWINGS

The foregoing and other objects, features and advantages of the invention will be

15 apparent from the following more particular description of preferred embodiments of the invention, as illustrated in the accompanying drawings in which like reference characters refer to the same parts throughout the different views. The drawings are not necessarily to scale, emphasis instead being placed upon illustrating the principles of the invention.

FIG. 1 is a perspective view of the apparatus of this invention before heating and

20 calendaring;

FIG. 2A is a perspective view of the apparatus of this invention after heating a calendaring;

FIG. 2B is a perspective view of the apparatus of this invention after heating and calendaring with a cover sheet;

25 FIG. 3A is a perspective view of the apparatus of this invention in a square or rectangular containment structure showing the creases of the pleated structure;

FIG. 3B is a top view of the apparatus of this invention showing its pleated structure;

FIG. 4 is a top view of the apparatus of this invention with a high first pass efficiency multi-pleat pack panel filter in a square or rectangular containment structure;

FIG. 5A is a top view of the apparatus of this invention in a radially pleated cylindrical containment structure;

5 FIG. 5B is a top view of the apparatus of this invention in a media-wrapped cylindrical filter; and

FIG. 6 is a perspective view of a process of producing a filter of the invention.

FIG. 7 is a pleated filter made in accordance with the invention.

FIG. 8 is a graphical illustration comprising the base removal efficiency of filters
10 previously available and a filter made in accordance with the invention.

FIG. 9 is a process for fabricating a filter in accordance with a preferred embodiment of the invention.

FIG. 10 illustrates an example of a three dimensional filter fabricated in
accordance with the process.

15

DETAILED DESCRIPTION OF THE INVENTION

Referring to FIG. 1, a portion of a composite 16 is shown. The composite 16 has a cover sheet 66 and a middle layer 62. In a preferred embodiment, the cover sheet 66 is a polyester non woven having a binder to fiber ratio of 55/44 and a thickness of 0.024
20 inches. The middle layer 62 is air-laid polyester non woven having a thickness of 0.25 inches and binder to fiber ratio of 35%/65%. The composite is impregnated with a porous acidic polymer material that binds readily with molecular bases in air flowing through the filter.

The structure of FIG.2A can be used directly in this form as the composite filter
25 element. The composite 16, in a preferred embodiment employs a second cover sheet 80, provided on the surface of middle layer 62, opposite to the first cover sheet 66 backing 12, as shown in FIG. 2B. Alternatively, a second cover sheet 14a, can be provided over the backing layer 12, as shown in FIG. 2C. The cover sheet can be a filtering or non-filtering non-woven polyester, polyamide or polypropylene material or other similar

materials. If the cover sheet is a filtering material, it serves to provide some filtering of the air entering the composite structure for removal of particulate materials in the air stream. The cover can also serve to retain the porous acidic polymer material such as a sulfonated divinyl benzene styrene copolymer, which can be in bead form, within the middle layer or batting 62. The cover sheets can also be chemically inert materials such as polypropylene.

The composite 16, can be contained within any suitable container or frame work for installation in an intended position for filtering operation, typically in the form of a removable or replaceable filter element. For many purposes, it is preferable to increase the surface area of the filter material exposed to an incident air flow, and for this purpose the composite can be pleated to provide the increased surface area.

One embodiment is shown in FIG. 3A, in which the composite material forms an air filter 15 or 17. The filter material is pleated into an accordion like structure 19 as shown in FIG 3B, contained within a square or rectangular container 18 having a front 21, and back 23, which are open to an air stream shown by arrow 22. The pleating 20 is substantially perpendicular to the air flow. FIG. 3A shows the structure in a front or back view. FIG. 3B shows a cutaway top view of a filter structure.

An alternative embodiment is shown in FIG. 4 wherein a plurality of pleated composite elements 24, are sequentially disposed within container 18, to provide a multi-stage filter through which the air can pass. As in the above embodiment, the pleats 20, of the elements 24, are substantially perpendicular to the direction of air flow 22.

A further embodiment is shown in FIG. 5A, wherein the composite structure 16, is disposed in a cylindrical configuration and retained within a cylindrical container 28. The pleats 20, are as described above, substantially perpendicular to a radially directed air flow. A further embodiment is shown in FIG. 5B wherein the composite structure is wound in a spiral configuration 30, contained within a generally cylindrical container 28.

In a preferred embodiment, adsorbent particles are evenly distributed throughout the non-woven or fiber matrix or polyester batting. An example of an adsorbent particle includes but is not limited to sulfonated divinyl benzene styrene copolymer.

In a preferred embodiment, the ion exchange strongly acidic preliminary catalyst
5 has the important properties including a particle size of between 0.3 and 1.2 mm, a porosity of approximately 0.30 ml/g, and an average pore diameter of 250Å. The catalyst preferably has a higher porosity of up to 300 ml/g, or higher. In addition in a preferred embodiment has the properties of concentration of acid site of approximately 1.8 meq/ml and surface area of 45 m²/g. One such catalyst is sold under the trade name
10 AMBERLYST®15 DRY or AMERLYST®35DRY by Rohm and Haas.

Overall, the dry processing of the fiber matrix, which includes the combination of the fluidized bed sulfonated divinyl benzene styrene copolymer deposition process, the inherent stratification of the batting's density, and the even distribution of the sulfonated divinyl benzene styrene copolymer particles as well as stratification of the sulfonated
15 divinyl benzene styrene copolymer particle size, allows for a fabric architecture having an increased bed depth at a very low pressure drop, which is highly desirable due to its high first pass efficiency coupled with its low operating costs.

The term "efficiency" as employed herein is defined by the formula $X-Y/X$ wherein X is the upstream concentration of pollutant, and Y is the downstream
20 concentration of pollutant.

It is recognized that the filter can have a mix of an activated carbon and the preliminary catalyst material discussed above. This combination has sufficient porosity and strongly acidic groups to provide east permanent removal of medium and strong basis and sufficient retention of weak bases form the airborne base contaminants. The
25 filter can also include a porous polymer material.

The filter as described is employed in filtering the air in environments such as semiconductor fabrication systems where there is a requirement for uncontaminated air of high quality.

Referring to Fig. 6, the middle air-laid polyester non woven lay 62 is collated to a cover sheet 66. The adsorbent particles 60 are positioned on a fiber matrix 62 from a fluidized bed 64. The sulfonated divinyl benzene styrene particles 60 are evenly stratified throughout the depth of the batting 62. As discussed above, an increased bed
5 depth of adsorbent particles distributed throughout the batting is highly desirable as it increases residence time, creases exposure of the adsorbent particle surfaces, provides a low pressure drop, as well as substantially increasing the lifetime of the filter.

The adsorbent particles 60 distributed in the matrix 62 are then heated, preferable using two zones 68, 70 of infrared energy at different wavelengths. The batting 62 is
10 heated to an overall average temperature of between 250° and 350°F.

The infrared energy causes the adsorbent particles to adhere to the batting at points where the particles contact the batting. This procedure avoids the necessity of raising the temperature of the entire batting to a point at, or near, the melting point of the polyester batting, which could cause the batting to melt and collapse thereby encasing the
15 particles and destroying their chemical activity.

The batting 62 is then calendared using a pair of calender rolls 76, 78. The first of these rolls 76 (Heated Steel Roller) can be temperature controlled which allows the heating and calendaring steps to be carried out at a steady temperature of around 140°, and prevents overheating and subsequent melting of cover sheet and prevents over
20 calendaring of the fabric. The second roll, roll 78, is a rubber roll having a durometer that avoids crushing of the adsorbent particles.

In Figure 6, Middle Layer (62) can have the following specifications: Air-Laid Polyester Non Woven 100% 15 Denier Fiber. The Binder consists of a Fiber Ratio of 35% to 65%, Binder to Fiber. The weight is 6.5 oz. per linear yard at a 52 inch width.
25 The thickness is 0.25 inches.

The cover sheet (66 and 80) can have the following specifications: Polyester Non Woven 100% 2.25 Denier Fiber. The Binder consists of a Fiber Ratio of 55g/45g. The thickness is .024 inches and the weight is 1.75 oz./yd².

Furthermore, when the temperature controlled roller 76 is used, the pressure at which the batting is 2000 pounds across the 26 inch distance. Higher calendaring pressures can crush the particles particularly when those particles are activated carbon based, thereby forming dust, which cannot be retained in the filter composite and can consequently pass into the gas stream.

In addition, a synthetic non-woven cover sheet 80, which helps to maintain the sulfonated divinyl benzene styrene copolymer in the batting, may be calendared with the batting 62, as discussed above. After the filter is formed, gussets or spacers are placed in the filter. The filter is sealed into a metal box.

Optionally, the material may be conducted over an upper roller 84 to facilitate cooling the material prior to further processing. The method of manufacture for an activated carbon filter is described in detail in U.S. Patent No. 5,582,865 titled "Non-Woven Filter Composite". The entire contents of this patent is incorporated herein by reference.

While the above described method is a preferred method of creating the filter, it is recognized that other techniques can be used. Some of these techniques include those developed by Hoechst such as that described in U.S. Patent No. 5,605,746, the entire contents of which is incorporated herein by reference or KX Media. The common feature in all these methods are the incorporation of a chemically active sorbent into a porous media structure.

A pleated filter structure 220 using the porous acidic polymer of the present invention is illustrated in FIG. 7. This is a pleated system open on both sides of a rectangular frame 228 with a length 222, width 224 and depth such that it can be used as a replacement filter in stack filter systems. The filter has a removal efficiency of over 99% at 1000 ppb.

FIG. 8 graphically illustrates the removal efficiency for three different filters. The graphs represent removal efficiency as a function of time at 20 ppm of NH_3 concentration upstream from the filter. Filter size is $\sim 12'' \times 12'' \times 6''$. Air flow is ~ 100 cfm.

Considering service life data only, it appears that filter #3 performed best. However, if

additional data is considered, the conclusion is not so simple. Pressure drop of filter #1 was 0.2"WC; for filter #2 was 0.3"WC; and for filter #3 was 1.0"WC. Filters #1 and #2 are very close to tool manufacturer's specifications, but #3 creates an excessive pressure drop that interferes with tool's proper ECU functioning. Excessive pressure drop is
5 undesirable for multiple reasons. For example, it increases fan load and power consumption, reduces airflow through the tool and positive pressure inside the enclosure. Thus filter #1 made in accordance with the present invention provided a substantial improvement in service life while providing a pressure drop that is compatible with tool operation.

10 Another preferred embodiment of the invention involves the fabrication of high surface area filter elements using a three dimensional printing technique as described in U.S. Patent Nos. 5,204,055, 5,340,656, and 5,387,380, the entire contents of these patents being incorporated herein by reference.

Such a method of fabrication of a filter element is illustrated in connection with
15 FIG. 9. The process 200 includes forming a three dimensional model 202 of the filter element such that the dimensions are well defined. The first layer of the powder material used to form the filter is placed 204 the printer apparatus. A binder is then delivered 206 onto the powder material resulting in the binding of selected regions thereof. Steps 204 and 206 are repeated a number of times until the high surface area filter is formed.
20 Finally, the excess material is removed 210. An illustrative example of a high surface area filter made in accordance with this method is shown in the example 240 of FIG. 10. The binder can be an acid polymerizable or acid cross linkable liquid.

While this invention has been particularly shown and described with references to preferred embodiments thereof, it will be understood by those skilled in the art that
25 various changes in form and details may be made therein without departing from the spirit and scope of the invention as defined by the appended claims.